



PROMAFOUR®-GLUE 1000 is a ready for use refractory silicate based glue which resists to temperatures up to 1000 °C.

PROMAFOUR®-GLUE 1000 is the appropriate product for the construction of a PROMAFOUR® mantelpiece and is the ideal solution for fireplaces.

PROMAFOUR®-GLUE 1000 can also be used for bonding ropes and insulation materials onto glass fibre, mineral wool and calcium silicate as well as metal, stone or plasterboard.

Properties & advantages

- Ready for use
- High adhesion strength on cast iron, steel and refractory materials
- Fine pasty consistency
- Permanent high temperature resistance up to 1000 °C
- Quick bonding and thus suitable as auxiliary product when assembling

Typical applications

- PROMAFOUR® construction boards
- PROMASIL®-1000L insulation boards
- PROMAFOUR®-HTI 1100 BLANKETS
- Glass fibre, mineral wool, metal, stone and plasterboard

Working, machining & installation

- The surface has to be clean (free from fat, moisture and dust)
- Homogenise before usage
- Apply 500 g/m² (depending on the nature of the materials and application technique usage could be higher)
- Apply single or double layers
- Put both parts together and position correctly
- Press both parts together for a few minutes
- Drying and hardening takes at least 12 to 24h
- Do not use at temperatures below 7 °C





Technical data

Brand	PROMAFOUR®-GLUE 1000
Colour	White/Grey
Consistency	Pasty
Classification temperature	1000 °C
Processing temperature	15 - 30 °C
Hardening	Between 12 - 24h
Treatment	Dry, dust-free, grease-free surface
Ambient temperature for use	15 - 30 °C
Viscosity	6300 +/- 500 cPs
Fire-resistance	Non-combustible
Density	1.60 +/- 0.5
Storage	Original sealed cartridge, between 5 - 35 °C: max. 12 months

Product dimensions & size availability

Standard sizes
310ml / 15ml cartridge
1.5kg bucket
15kg bucket

www.promat-hpi.com

The information contained in this datasheet/brochure is intended to assist in designing with Microtherm products. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this datasheet will be achieved by a user for a particular purpose. The user is responsible for determining the suitability of Microtherm products for each application. No known health hazards in normal use.